

Technical data

Categories No: TNRGOH

Name: -OH Functionalized Graphene

Purity: >98wt%


layers: <10

Thickness: 0.55-3.74nm



Diameter: 0.5-3 μ m


Oxygen content: >10wt%

1、SEM of -OH Functionalized Graphene



2. XPS of -OH Functionalized Graphene





| Components | Area(CPS) | Contents | Components |
|------------|----------------|-------------|---------------|
| C | 72453.7 | 0.25 | 86.63% |
| O | 29531.8 | 0.66 | 13.37% |